

**SAM™ Data Sheet SAM-1064-10-5ps-x,  $\lambda = 1064$  nm**

Laser wavelength	$\lambda = 1064$ nm
High reflection band	$\lambda = 1000 .. 1070$ nm
Absorbance	$A_0 = 10$ %
Modulation depth	$\Delta R = 6$ %
Non-saturable loss	$A_{ns} = 4$ %
Saturation fluence	$\Phi_{sat} = 35$ $\mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau = 5$ ps
Damage threshold	$\Phi = 3$ $\text{mJ}/\text{cm}^2$
Chip area	4.0 mm x 4.0 mm; other dimensions on request
Chip thickness	450 $\mu\text{m}$
Protection	the SAM is protected with a dielectric front layer

Mounting option **x** denotes the type of mounting as follows:

- x = 0** unmounted
- x = 12.7 g** glued on a copper heat sink with 12.7 mm  $\varnothing$
- x = 25.4 g** glued on a copper heat sink with 25.4 mm  $\varnothing$
- x = 12.7 s** soldered on a copper heat sink with 12.7 mm  $\varnothing$
- x = 25.4 s** soldered on a copper heat sink with 25.4 mm  $\varnothing$
- x = 25.0 w** soldered on a water cooled copper heat sink with 25.0 mm  $\varnothing$
- x = FC** mounted on a 1 m single mode fiber with FC connector

**Low intensity spectral reflectance**

