



## SAM<sup>TM</sup> Data Sheet SAM-1064-22-47ps-x, $\lambda$ = 1064 nm

Laser wavelength  $\lambda = 1064 \text{ nm}$ 

High reflection band  $\lambda$  = 1020 .. 1100 nm

Reflectance at 808 nm R<sub>808</sub> = 50 % Absorbance  $A_0 = 22 \%$  $\Delta R = 13 \%$ Modulation depth  $A_{ns} = 9 \%$ Non-saturable loss

 $\Phi_{\text{sat}} = 49 \, \mu \text{J/cm}^2$ Saturation fluence

 $\tau \sim 47 \text{ ps}$ Relaxation time constant

 $\Phi = 2 \text{ mJ/cm}^2$ Damage threshold

4.0 mm x 4.0 mm; other dimensions on request Chip area

Chip thickness 450 µm

Dielectric coating HR @ 808 nm and AR @ 1064 nm


Mounting option **x** denotes the type of mounting as follows:

 $\mathbf{x} = 0$ unmounted


x = 12.7 gglued on a copper heat sink with 12.7 mm Ø x = 25.4 gglued on a copper heat sink with 25.4 mm  $\varnothing$ x = 12.7 ssoldered on a copper heat sink with 12.7 mm  $\varnothing$ x = 25.4 ssoldered on a copper heat sink with 25.4 mm  $\varnothing$ 

soldered on a water cooled copper heat sink with 25.4 mm  $\varnothing$ x = 25.4 wmounted on a 1 m monomode fiber cable with FC connector x = FC


## Low intensity spectral reflectance







## **Saturation measurement**





## **Pump-probe measurement**

