



## SAM<sup>TM</sup> Data Sheet SAM-1064-55-10ps-x, $\lambda$ = 1064 nm

 $\lambda = 1064 \text{ nm}$ Laser wavelength

High reflection band  $\lambda$  = 1010 .. 1110 nm

Absorbance  $A_0 = 55 \%$  $\Delta R = 40 \%$ Modulation depth Non-saturable loss  $A_{ns} = 15 \%$ 

 $\Phi_{\text{sat}} = 35 \, \mu \text{J/cm}^2$ Saturation fluence

Relaxation time constant  $\tau \sim 10 \text{ ps}$ 

 $\Phi$  = 600  $\mu$ J/cm<sup>2</sup> Damage threshold

Chip area 4.0 mm x 4.0 mm; other dimensions on request

Chip thickness 450 µm

Protection the SAM is protected with a dielectric front layer

Mounting option **x** denotes the type of mounting as follows:

unmounted  $\mathbf{x} = 0$ x = 12.7 gglued on a copper heat sink with 12.7 mm Ø x = 25.4 gglued on a copper heat sink with 25.4 mm Ø

x = 12.7 ssoldered on a copper heat sink with 12.7 mm Ø x = 25.4 ssoldered on a copper heat sink with 25.4 mm Ø

x = 25.0 wsoldered on a water cooled copper heat sink with 25.0 mm  $\varnothing$ x = FCmounted on a 1 m single mode fiber with FC connector

## Low intensity spectral reflectance and dispersion coefficient D<sub>2</sub>

