

### SAM™ data sheet SAM-1550-17-1.5ps-x, $\lambda = 1550$ nm

Laser wavelength	$\lambda = 1550$ nm
High reflection band	$\lambda = 1470 .. 1610$ nm
Absorbance	$A_0 = 17$ %
Modulation depth	$\Delta R = 10$ %
Non-saturable loss	$A_{ns} = 7$ %
Saturation fluence	$\Phi_{sat} = 40$ $\mu\text{J}/\text{cm}^2$
Damage threshold	$\Phi_{dam} = 1.5$ $\text{mJ}/\text{cm}^2$
Relaxation time constant	$\tau = 1.5$ ps
Chip area	4.0 mm x 4.0 mm; other dimensions on request
Chip thickness	450 $\mu\text{m}$
Protection	the SAM is protected with a dielectric front layer
Mounting option <b>x</b> denotes the type of mounting as follows:	
<b>x</b> = 0	unmounted
<b>x</b> = 12.7 g	glued on a gilded Cu-cylinder with 12.7 mm $\varnothing$ and 4 mm $\varnothing$ center hole
<b>x</b> = 25.0 g	glued on a gilded Cu-cylinder with 25. mm $\varnothing$ and 4 mm $\varnothing$ center hole
<b>x</b> = 25.4 g	glued on a gilded Cu-cylinder with 25.4 mm $\varnothing$ and 4 mm $\varnothing$ center hole
<b>x</b> = FC	mounted on a 1 m single mode fiber cable with FC connector

#### Low intensity spectral reflectance and GVD

