

SAM™ data sheet SAM-1550-17-2ps-x, $\lambda = 1550$ nm

Laser wavelength	$\lambda = 1550$ nm
High reflection band (R > 82%)	$\lambda = 1480 .. 1580$ nm
Absorbance	$A_0 = 17$ %
Modulation depth	$\Delta R = 10$ %
Non-saturable loss	$A_{ns} = 7$ %
Saturation fluence	$\Phi_{sat} = 50$ $\mu\text{J}/\text{cm}^2$
Damage threshold	$\Phi_{dam} = 1.5$ mJ/cm^2
Relaxation time constant	$\tau = 2$ ps
Chip area	4.0 mm x 4.0 mm; other dimensions on request
Chip thickness	450 μm
Protection	the SAM is protected with a dielectric front layer

Mounting option **x** denotes the type of mounting as follows:

- x** = 0 unmounted
- x** = 12.7 g glued on a gilded Cu-cylinder with 12.7 mm \varnothing and 4 mm \varnothing center hole
- x** = 25.0 g glued on a gilded Cu-cylinder with 25. mm \varnothing and 4 mm \varnothing center hole
- x** = 25.4 g glued on a gilded Cu-cylinder with 25.4 mm \varnothing and 4 mm \varnothing center hole
- x** = FC mounted on a 1 m single mode fiber cable with FC connector

Low intensity spectral reflectance



