

SAM™ data sheet SAM-1550-20-10ps-x, $\lambda = 1550$ nm

Laser wavelength	$\lambda = 1550$ nm
High reflection band	$\lambda = 1450 .. 1580$ nm
Absorbance	$A_0 = 20$ %
Modulation depth	$\Delta R = 12$ %
Non-saturable loss	$A_{ns} = 8$ %
Saturation fluence	$\Phi_{sat} = 40$ $\mu\text{J}/\text{cm}^2$
Damage threshold	$\Phi = 1$ mJ/cm^2
Relaxation time constant	$\tau = 10$ ps
Chip area	4.0 mm x 4.0 mm; other dimensions on request
Chip thickness	450 μm
Protection	the SAM is protected with a dielectric front layer

Mounting option **x** denotes the type of mounting as follows:

- x** = 0 unmounted
- x** = 12.7 g glued on a gilded Cu-cylinder with 12.7 mm \varnothing and 4 mm \varnothing center hole
- x** = 25.0 g glued on a gilded Cu-cylinder with 25. mm \varnothing and 4 mm \varnothing center hole
- x** = 25.4 g glued on a gilded Cu-cylinder with 25.4 mm \varnothing and 4 mm \varnothing center hole
- x** = FC mounted on a 1 m single mode fiber cable with FC connector

Low intensity spectral reflectance

