

SAM™ Data Sheet SAM-1040-10-1ps-x, $\lambda = 1040$ nm

Laser wavelength	$\lambda = 1040$ nm
High reflection band (R > 88%)	$\lambda = 1010 \dots 1100$ nm
Absorbance	$A_0 = 10$ %
Modulation depth	$\Delta R = 6$ %
Non-saturable loss	$A_{ns} = 4$ %
Saturation fluence	$\Phi_{sat} = 35$ $\mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau \sim 1$ ps
Damage threshold	$\Phi = 3$ mJ/cm^2
Chip area	4 mm x 4 mm; other dimensions on request
Chip thickness	450 μm ; optional: 150 μm on request
Protection	the SAM is protected with a dielectric front layer

Mounting option **x** denotes the type of mounting as follows:

- x** = 0 unmounted
- x** = 12.7 g glued on a copper heat sink with 12.7 mm \varnothing
- x** = 25.4 g glued on a copper heat sink with 25.4 mm \varnothing
- x** = 12.7 s soldered on a copper heat sink with 12.7 mm \varnothing
- x** = 25.4 s soldered on a copper heat sink with 25.4 mm \varnothing
- x** = 25.0 w soldered on a water cooled copper heat sink with 25.0 mm \varnothing
- x** = FC mounted on a 1 m single mode fiber with FC connector

Low intensity spectral reflectance and dispersion

