

## SAM™ Data Sheet SAM-1040-30-25ps-x, $\lambda = 1040 \text{ nm}$

Laser wavelength	$\lambda = 1040 \text{ nm}$
High reflection band	$\lambda = 1000 \text{ .. } 1100 \text{ nm}$
Absorbance	$A_0 = 30 \%$
Modulation depth	$\Delta R = 21 \%$
Non-saturable loss	$A_{ns} = 9 \%$
Saturation fluence	$\Phi_{sat} = 20 \mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau \sim 25 \text{ ps}$
Damage threshold	$\Phi = 2 \text{ mJ}/\text{cm}^2$
Chip area	4.0 mm x 4.0 mm; other dimensions on request
Chip thickness	450 $\mu\text{m}$
Protection	the SAM is protected with a dielectric front layer

Mounting option **x** denotes the type of mounting as follows:

<b>x</b> = 0	unmounted
<b>x</b> = 12.7 g	glued on a copper heat sink with 12.7 mm $\varnothing$
<b>x</b> = 25.4 g	glued on a copper heat sink with 25.4 mm $\varnothing$
<b>x</b> = 12.7 s	soldered on a copper heat sink with 12.7 mm $\varnothing$
<b>x</b> = 25.4 s	soldered on a copper heat sink with 25.4 mm $\varnothing$
<b>x</b> = 25.4 w	soldered on a water cooled copper heat sink with 25.4 mm $\varnothing$
<b>x</b> = FC	mounted on a 1 m monomode fiber cable with FC connector

### Low intensity spectral reflectance

