

**SAM™ Data Sheet SAM-1040-32-5ps-x,  $\lambda = 1040$  nm**

Laser wavelength	$\lambda = 1040$ nm
High reflection band	$\lambda = 1010 \dots 1080$ nm
Absorbance	$A_0 = 32$ %
Modulation depth	$\Delta R = 18$ %
Non-saturable loss	$A_{ns} = 14$ %
Saturation fluence	$\Phi_{sat} = 85 \mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau \sim 5$ ps
Damage threshold	$\Phi = 2 \text{ mJ}/\text{cm}^2$
Chip area	4.0 mm x 4.0 mm; other dimensions on request
Chip thickness	450 $\mu\text{m}$
Protection	the SAM is protected with a dielectric front layer

Mounting option **x** denotes the type of mounting as follows:

- x = 0** unmounted
- x = 12.7 g** glued on a gold plated Cu-cylinder with 12.7 mm  $\varnothing$
- x = 25.4 g** glued on a gold plated Cu-cylinder with 25.4 mm  $\varnothing$
- x = 12.7 s** soldered on a gold plated Cu-cylinder with 12.7 mm  $\varnothing$
- x = 25.4 s** soldered on a gold plated Cu-cylinder with 25.4 mm  $\varnothing$
- x = FC** mounted on a 1 m monomode fiber cable with FC connector

**Low Intensity Spectral Reflectance**

