


Kokyo 株式会社光響 http://www.symphotony.com/メール:info@symphotony.com

## SAM™ Data Sheet SAM-1040-5-1ps-x, λ = 1040 nm

Laser wavelength	$\lambda = 1040 \text{ nm}$
High reflection band (R > 90%)	$\lambda = 1020 1100 \text{ nm}$
Absorbance	A <sub>0</sub> = 5 %
Modulation depth	$\Delta R = 3 \%$
Non-saturable loss	A <sub>ns</sub> = 2 %
Saturation fluence	$\Phi_{sat}$ = 45 µJ/cm <sup>2</sup>
Relaxation time constant	τ ~ 1 ps
Damage threshold	$\Phi = 4 \text{ mJ/cm}^2$
Chip area	4 mm x 4 mm; other dimensions on request
Chip thickness	450 µm
Protection	the SAM is protected with a dielectric front layer
-	unmounted
0	glued on a copper heat sink with 12.7 mm $\varnothing$


x = 12.7  g	greed on a copper near sink with 12.7 mm $\oslash$
<b>x</b> = 25.4 g	glued on a copper heat sink with 25.4 mm $arnothing$
<b>x</b> = 12.7 s	soldered on a copper heat sink with 12.7 mm $arnothing$
<b>x</b> = 25.4 s	soldered on a copper heat sink with 25.4 mm $arnothing$
<b>x</b> = 25.0 w	soldered on a water cooled Cu-cylinder with 25.0 mm $arnothing$
x = FC	mounted on a 1 m singlemode fiber cable with FC connector




2



**Saturation measurement** 





www.batop.de