

**SAM™ Data Sheet SAM-1040-7-1ps-x,  $\lambda = 1040$  nm**

Laser wavelength	$\lambda = 1040$ nm
High reflection band (R > 90%)	$\lambda = 1020 .. 1100$ nm
Absorbance	$A_0 = 7$ %
Modulation depth	$\Delta R = 4$ %
Non-saturable loss	$A_{ns} = 3$ %
Saturation fluence	$\Phi_{sat} = 50$ $\mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau \sim 1$ ps
Damage threshold	$\Phi = 4$ $\text{mJ}/\text{cm}^2$
Chip area	4 mm x 4 mm; other dimensions on request
Chip thickness	450 $\mu\text{m}$
Protection	the SAM is protected with a dielectric front layer

Mounting option **x** denotes the type of mounting as follows:

- x = 0** unmounted
- x = 12.7 g** glued on a copper heat sink with 12.7 mm  $\varnothing$
- x = 25.4 g** glued on a copper heat sink with 25.4 mm  $\varnothing$
- x = 12.7 s** soldered on a copper heat sink with 12.7 mm  $\varnothing$
- x = 25.4 s** soldered on a copper heat sink with 25.4 mm  $\varnothing$
- x = 25.0 w** soldered on a water cooled Cu-cylinder with 25.0 mm  $\varnothing$
- x = FC** mounted on a 1 m singlemode fiber cable with FC connector

**Low intensity spectral reflectance and dispersion GDD**

