


SAM™ Data Sheet SAM-1300-12-10ps-x, $\lambda = 1300$ nm

Laser wavelength	$\lambda = 1300$ nm
High reflection band	$\lambda = 1240 \dots 1340$ nm
Absorbance	A = 12 %
Saturation fluence	$\Phi_{\text{sat}} = 60 \mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau \sim 10$ ps
Modulation depth	$\Delta R = 7$ %
Damage threshold	$\Phi = 900 \mu\text{J}/\text{cm}^2$
Chip area	4.0 mm x 4.0 mm; other dimensions on request
Chip thickness	450 μm
Protection	the SAM is protected with a dielectric front layer

Mounting option **x** denotes the type of mounting as follows:

- x** = 0 unmounted
- x** = 12.7 g glued on a gold plated Cu-cylinder with 12.7 mm \varnothing
- x** = 25.4 g glued on a gold plated Cu-cylinder with 25.4 mm \varnothing
- x** = 12.7 s soldered on a gold plated Cu-cylinder with 12.7 mm \varnothing
- x** = 25.4 s soldered on a gold plated Cu-cylinder with 25.4 mm \varnothing
- x** = 25.0 w soldered on a water cooled Cu-cylinder with 25.0 mm \varnothing
- x** = FC mounted on a 2 m monomode fiber cable with FC connector

Spectral reflectance



SAM 424-IIa