

SAM™ Data Sheet SAM-980-3-1ps-x, $\lambda = 980$ nm

Laser wavelength	$\lambda = 980$ nm
High reflection band	$\lambda = 940 \dots 1000$ nm
Saturable absorptance	$A_0 = 3$ %
Saturation fluence	$\Phi_{\text{sat}} = 70$ $\mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau \sim 1$ ps
Modulation depth	$\Delta R = 1.8$ %
Non-saturable loss	$A_{\text{ns}} = 1.2$ %
Damage threshold	$\Phi = 1.2$ mJ/cm ²
Chip area	4.0 mm x 4.0 mm, other dimensions on request
Chip thickness	450 μm

Mounting option **x** denotes the type of mounting as follows:

x = 0	unmounted
x = 12.7 g	glued on a gold plated Cu-cylinder with 12.7 mm \varnothing
x = 25.4 g	glued on a gold plated Cu-cylinder with 25.4 mm \varnothing
x = 12.7 s	soldered on a gold plated Cu-cylinder with 12.7 mm \varnothing
x = 25.4 s	soldered on a gold plated Cu-cylinder with 25.4 mm \varnothing
x = FC	mounted on a 1 m monomode fiber cable with FC connector

Low intensity spectral reflectance

